



Description

WS 3622 G restores stainless steel surfaces damaged, rusted or soiled by limescale build-up or other environmental factors and leaves long-lasting protection.

The effect of **WS 3622 G** is based on a deep cleaning of the stainless steel, restoring the original surface finish and significantly increasing its resistance to corrosion.

Features

- Cleaning and protection in one product.
- Does not attack other materials.
- · Restores the original surface finish.
- It is not a hazardous product.

Applications

- Superficial cleaning of rust, lime and saltpetre stains.
- Regenerates the passive layer (it is not a Passivant).

Instructions for use

> Security:

Refer to the product safety data sheet.

> Application:

Areas where the product should not or cannot be applied shall be sealed or protected by a plastic material.

The part must not be exposed to direct sunlight during the process, to avoid possible staining of the surface.

The temperature of the surface to be treated must be between +5°C and

+30°C. The product is ready to use, without dilution.

The product can be applied by roller, cloth, spraying and dipping.

The application time will depend on the condition of the surface to be treated.

For stubborn impurities, several applications are required, preferably using a coarse, soft cloth to enhance the cleaning effect.

After treatment, the surface must be rinsed with clean water.







Waste Management:

The wastewater from the process is strongly acidic and contains dissolved metal ions. The concentration of metal ions is normally below the legal limit values. A pH neutralisation treatment can be carried out for subsequent delivery to a waste manager. The waste must be treated as hazardous waste according to legal requirements.

> Storage:

Store in accordance with local legislation. Observe label instructions. Store containers between 5 and 25°C, in a dry, well-ventilated place, away from heat sources and direct sunlight. Keep away from sources of ignition. Keep away from oxidizing agents and strongly acidic or alkaline materials. Do not smoke. Keep away from unauthorised persons. After opening, containers should be carefully resealed and placed upright to prevent spillage.

Certifications/Specifications

Conforms to ASTM A380.

Technical Data

Property	Specification/Method	Value
Reference		WS 3622 G
Aspect		Liquid
Colour		Colourless
Density at 20°C		1,09 Kg/l
100% pH		0 - 1
Surface tension at 20°C		Not applicable
Minimum temperature		5°C
Maximum temperature		30°C
Freezing point		Not applicable
Flash point		Not applicable